Thermal Management Solutions

Technical Data Sheet



GF300 Gap Filler

GF300 is a two part, liquid silicone based gap filler, which provides excellent thermal performance and can be cured at room temperature or accelerated with heat. After curing GF300 forms a low modulus elastomer preventing the 'pump-out phenomenon'.

- Soft and compliant for low stress applications
- Low viscosity; easy to dispense
- High thermal conductivity
- Low modulus elastomer, prevents 'pump-out'

Approvals	RoHS Compliant (2015/863/EU):	Yes
Typical Properties	·	
Liquid Properties:	Base Material Colour Part A Colour Part B Mixed System Viscosity (mPa s @ 25°C) Mix Ratio Gel Time (25°C) Cure Time (25°C) Cure Time (60°C) Cure Time (100°C)	Silicone Blue White 140 000 1:1 60 minutes 12 hours 80 minutes 15 minutes
Cured System:	Cured Density (g/ml) Thermal Conductivity (W/m.K) Colour Temperature Range (°C) Dielectric Strength (kV/mm) Volume Resistivity (ohm-cm) Shore Hardness @ 25°C Flame Retardancy Weight Loss after 96 hours @ 100°C	3.0 3.0 Pale Blue -50 to 200 11 10 ¹⁴ 55 Shore 00 Meets UL94 V-0 < 0.10%

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.



DescriptionPackingOrder CodeShelf LifeGF300 Gap Filler400ml Two Part CartridgeGF300_400ML9 months

Directions for Use

Ensure surfaces are clean, dry and free from grease and dust before use. Certain materials like curing agents and plasticisers can inhibit curing of silicone compounds. These chemicals include:

- Organotin and other organometallic compounds.
- Silicone rubber containing organotin catalysts.
- Sulphur and other sulphur containing materials, Amines, urethanes or amine containing materials.
- Unsaturated hydrocarbon plasticisers.

Additional Information

Cleaning: GF300 can be removed easily up to 1 hour after application with an approved solvent

such as IPA.

Storage: Keep lids tightly sealed. Store under ambient conditions.

Health & Safety: Always refer to the Health & Safety data sheet before use. These can be downloaded

from www.electrolube.com

Revision 3: January 2020